



# nax CRYSTAL 9905

## MIRROR IMAGE CLEAR 2K 2:1

Innovative high solid mirror like finish with incorporation of CyGlaz technology to integrate superb toughness, high flexibility and excellent chemical resistance. The product is designed to exhibit excellent mar and scratch resistance to withstand day to day wear and tear to ensure a long lasting beautiful look.

### FEATURES & BENEFITS

- Superb scratch resistance
- Self healing re-flow characteristics
- Mirror like reflective finish
- Long lasting durability
- Care-free maintenance





## Suitable Substrates

nax Premila 8000 Basecoat



2 nax Crystal 9905 Mirror Image Clear 2K 2:1  
1 nax Crystal 905 2K Hardeners



**Spray-gun setup:**  
Gravity fed 1.3-1.4mm

**Application Pressure:**  
1.7-2.2 bar (28-30 psi) At spray-gun air inlet  
HVLP max 0.6-0.7 bar (8-10 psi) at the air cap



1½-2 coats



20-30 µm/coat



**Between coats:**  
10-15min. at 20°C (70°F)

**Before 60°C(140°F) baking:**  
15min. at 20°C (70°F)



	20°C (70°F)	30°C (86°F)	40°C (100°F)	60°C (140°F)	Infra-Red
Dust dry	90 min.	45 min.	30 min.	n/a	
Dry to handle	10 hrs.	4-5 hrs.	3 hrs.	45 min.	4+8 min.
Dry to polish	10 hrs.	5 hrs.	4 hrs.	2 hrs. after cooldown	



nax Crystal 9905 Mirror Image Clear 2K 2:1 4 years  
nax Crystal 905 2K Hardener 2 years



**Use suitable respiratory protection**  
Use air fed mask at all times. Refer to applicable AS/NZS Standards

For detailed information, please refer to the relevant TDS. Visit: [nipponpaintautomotive.com.au](http://nipponpaintautomotive.com.au)



Nippon Paint products are supplied in Australia by Dulux Australia, a division of DuluxGroup (Australia) Pty Ltd, trading as Dulux Auto Refinish Coatings.