

Description


Nax Pro LV 4200 flexible Additive Gives flexibility to the paint to suit application on flexible surfaces. Mainly used in paint application on plastic parts. Can be used also to elasticise paint coatings on the metal to eliminate stone chipping.

Suitable Substrates

Primer Surfacer

Topcoats

Clearcoats



Ready to use



Flexible Additive use mixture of the Topcoats including Hardener and Thinner 10 – 30% maximum
Example : 1Litter Mixture of Topcoats with Hardener and Thinner add 10% Flexible Additive 100ml




Spray-gun setup:
Gravity fed | 1.2-1.4 mm

Application Pressure:

1.7-2.2 bar | 28-30 psi | At spray-gun air inlet
HVLP max 0.6-0.7 bar(8-10 psi) at the air cap



Application With :
Primer Surfacer Clearcoats, and Topcoats



Primer Surfacer
Clearcoats, Topcoats

Health & Safety



Use suitable personal protection equipment

- Always spray in Spraybooth
- Wear spray overall, solvent resistant gloves, and fresh air supply respiratory protection.

Equipment cleaning

Solvent borne guncleaners

Product storage

Minimum storage temperature:


5°C (41°F)

Maximum storage temperature:

40°C (100°F)

Notes: *Product shelf-life is determined when products are stored unopened at 20°C (70°F). Avoid extreme temperature fluctuation.*

Shelf life



Nax Pro LV4200 Anti-Silicone

24 months

DRAFT

Brand names and Logos mentioned in this data sheet are trademarks of or are licensed to NIPPON PAINT.

This product is for professional use only and not for sale to or use by the general public. Before using, read and follow all label and SDS precautions. The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, or as a warranty, nor the suitability of the products for a specific purpose. Standard drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only. In the light of experience and our policy of continuous product development, they may change without prior information and do not constitute the agreed contractual quality of the products (product specification).

It is always the responsibility of the recipient of our products to ensure that any proprietary rights, existing laws, legislation are observed and to take all necessary steps to fulfill the demands set out in the local rules and legislation. **THE LATEST VERSION OF TDS SUPERSEDES ALL PREVIOUS VERSIONS.**

BROUGHT TO YOU BY

Dulux

**AUTO REFINISH
COATINGS**