

CH02. Wet-on-Wet Primer Surfacer (3:1:0.9)

S1

Pro LV36xx Wet on Wet (S1)			
Comp.→	3601	360	5000
RFU (ml)↓	Surfacer	Hardener	Thinner
100	100	20	17
150	151	30	26
200	201	40	35
250	251	51	43
300	301	61	52
350	351	71	60
400	402	81	69
500	502	101	86
600	602	121	104
700	703	141	121

S2

Pro LV36xx Wet on Wet (S2)			
Comp.→	S2 mix	360	5000
RFU (ml)↓	Surfacer	Hardener	Thinner
100	101	20	17
150	151	30	26
200	201	40	35
250	252	51	43
300	302	61	52
350	352	71	60
400	403	81	69
500	503	101	86
600	604	121	104
700	705	141	121

S3

Pro LV3604 Wet on Wet (S3)			
Comp.→	3604	360	5000
RFU (ml)↓	Surfacer	Hardener	Thinner
100	99	20	17
150	149	30	26
200	198	40	35
250	248	51	43
300	298	61	52
350	347	71	60
400	397	81	69
500	496	101	86
600	595	121	104
700	694	141	121

S4

Pro LV36xx Wet on Wet (S4)			
Comp.→	S4 mix	360	5000
RFU (ml) ↓	Surfacer	Hardener	Thinner
100	102	20	17
150	152	30	26
200	203	40	35
250	254	51	43
300	305	61	52
350	356	71	60
400	407	81	69
500	508	101	86
600	610	121	104
750	762	152	129

S5

Pro LV36xx Wet on Wet (S5)			
Comp.→	S5 mix	360	5000
RFU (ml)↓	Surfacer	Hardener	Thinner
100	102	20	17
150	153	30	26
200	204	40	35
250	255	51	43
300	306	61	52
350	357	71	60
400	408	81	69
500	511	101	86
600	613	121	104
700	715	141	121

S6

Pro LV36xx Wet on Wet (S6)			
Comp.→	S6 mix	360	5000
RFU (ml)↓	Surfacer	Hardener	Thinner
100	103	20	17
150	154	30	26
200	205	40	35
250	257	51	43
300	308	61	52
350	359	71	60
400	410	81	69
500	513	101	86
600	616	121	104
700	718	141	121

S7

Pro LV36xx Wet on Wet (S7)			
Comp.→	3607	360	5000
RFU (ml)↓	Surfacer	Hardener	Thinner
100	103	20	17
150	154	30	26
200	206	40	35
250	257	51	43
300	309	61	52
350	360	71	60
400	411	81	69
500	514	101	86
600	617	121	104
700	720	141	121

Stir well after each added component!