

Description

nax Plastic Primer 1K is a single component ready to use plastic adhesion promoter designed to support the adhesion of primers/surfacers and 2K topcoats to common plastic parts found in automotive refinishes including Polypropylene and its blends. It also adheres various metal substrates.

Suitable Substrates

Polypropylene and its blends Polyester and epoxy laminates Steel, stainless, galvanized and aluminum

Notes: For best adhesion on metal substrates always use etch or epoxy primer.

Surface preparation



- ▶ Prior to any surface preparation, Remove oily contamination using nax Pro LV100 universal degreaser.
- ▶ Use clean quality rags or wiping towels, one for wetting and one for drying the surface.
- ▶ Apply sufficient degreaser to keep the surface wet.
- ▶ Wipe degreaser off before it can evaporate.




- ▶ Non primed new plastic (raw) → Use grey scuff pad with matting paste and warm water
- ▶ In case of plastic repair finish surface before priming, with: P320



- ▶ Prior to surfacer application on plastic, degrease the area using nax Pro LV300 Anti-Static Degreaser
- ▶ Prior to surfacer application on other surfaces, degrease with nax Pro LV100 Universal Degreaser
- ▶ Use clean quality rags or wiping towels, one for wetting and one for drying the surface
- ▶ Apply sufficient degreaser to keep the surface wet and wipe degreaser off before it can evaporate

Notes: Respect 100 grit maximum jump in dry sanding steps.

Product preparation




Ready to spray

Lightly agitate can before use.

Unused product can be returned into can

Viscosity (DIN 4 Cup)



20°C (70°F)
10-12 sec

30°C (86°F)
10-12 sec

40°C (100°F)
8-9 sec

Spray gun set-up / application pressure



Spray-gun type

Gravity

Nozzle size

1.2-1.4 mm
mm

Application pressure

Max 0.6-0.7 bar at the air cap (1.7-2.2 at inlet)
1.7-2.2 bar at the spray gun air inlet

Application



Number of coats: 1-2

Apply two medium wet coats over the sanded repair area, with 5-10 minutes flash off between coats

Re-coating time			
	20°C (70°F)	30°C (86°F)	40°C (100°F)
	15 minutes	10 minutes	5 minutes

Re-coating	
	With all nax Pro LV and Premila primer fillers and surfacers With all nax Premila 2 K topcoat systems
Notes:	To replicate OEM system and to achieve the highest quality always apply a w-o-w surfacer prior to topcoat.

Film thickness	
	1-2 Coats 5-10 µm/coat

Equipment cleaning	
Solvent borne guncleaners	

Solvent Content	
	2004/42/IIIB(e)(840)840
	The EU limit value for this product (product category: IIB.b) in ready to use form is max 840 g/liter
	The VOC content of this product in ready to use form is maximum 840 g/liter

Shelflife	
	nax Plastic Primer 1K
Minimum storage temperature:	5°C (41°F) Maximum storage temperature: 35°C (95°F)
Notes:	void extreme temperature fluctuation.

OAR.03.010. 300517
Professional Use Only

Brand names and Logos mentioned in this data sheet are trademarks of or are licensed to NIPPON PAINT.
 This product is for professional use only and not for sale to or use by the general public. Before using, read and follow all label and SDS precautions. The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, or as a warranty, nor the suitability of the products for a specific purpose. Standard drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only. In the light of experience and our policy of continuous product development, they may change without prior information and do not constitute the agreed contractual quality of the products (product specification).
 It is always the responsibility of the recipient of our products to ensure that any proprietary rights, existing laws, legislation are observed and to take all necessary steps to fulfill the demands set out in the local rules and legislation. **THE LATEST VERSION OF TDS SUPERSEDES ALL PREVIOUS VERSIONS.**