

Description

nax Pro LV4100 Anti-Silicone added to paint prevents the formation of craters (fish eyes/pinholes) in case the surface is contaminated with silicone or by greasing.

Suitable Products

Pro LV Clearcoats

Pro LV Topcoats




Anti-Silicone is added to the mixture of the RTS Pro LV clearcoats/topcoats in the amount of 2-4%
Example: To 1Lt RTS of Clearcoat with Hardener and Thinner, add 20ml (2%) Anti-Silicone



nax Pro LV4100 Anti-Silicone does not affect product drying



nax Pro LV4100 Anti-Silicone does not affect product spray viscosity, but may reduce paint flow at application.



nax Pro LV4100 Anti-Silicone does not affect pot life.



Use suitable respiratory protection

Nippon Paint Automotive Refinishes recommends the use of fresh air supply respirator.



nax Pro LV4100 Anti-Silicone

Minimum storage temperature:

5°C (41°F)

Maximum storage temperature:

35°C (95°F)

Notes:

Avoid extreme temperature fluctuation.

OAR.08.011. 181218
PROFESSIONAL USE ONLY

Brand names and Logos mentioned in this data sheet are trademarks of or are licensed to NIPPON PAINT.

This product is for professional use only and not for sale to or use by the general public. Before using, read and follow all label and SDS precautions. The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, or as a warranty, nor the suitability of the products for a specific purpose. Standard drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only. In the light of experience and our policy of continuous product development, they may change without prior information and do not constitute the agreed contractual quality of the products (product specification).

It is always the responsibility of the recipient of our products to ensure that any proprietary rights, existing laws, legislation are observed and to take all necessary steps to fulfill the demands set out in the local rules and legislation. **THE LATEST VERSION OF TDS SUPERSEDES ALL PREVIOUS VERSIONS.**

BROUGHT TO YOU BY

Dulux

**AUTOMOTIVE
COATINGS**